



TDS 10.12
FIRST CHOICE ACRYLIC PVA

DESCRIPTION:

First Choice Acrylic PVA is a lead free, durable and washable super acrylic coating providing a matt finish. Applied correctly First Choice Acrylic PVA will give a long lasting quality finish.

USES:

First Choice Acrylic PVA is an interior or exterior coating which is excellent for use on walls, ceilings or any similar type of masonry surface.

SPECIFICATION OR RECOMMENDED PAINT SYSTEM:

New Masonry Surfaces: All surfaces must be dry, free of dust, dirt, grease and other surface contamination. The standard conditions for the preparation of plastered, masonry surfaces must be adhered to. Apply one coat of First Choice Water Based Alkali Resistant Plaster Primer and allow to dry for 4-6 hours. Finish with at least 2 coats of First Choice Acrylic PVA to colour of choice allowing 4 hours drying time between coats.

Previously Painted Masonry Surfaces: Remove by scraping, wire brushing or sanding all soft powdered, blistered, loose or flaking paint. All surfaces should be washed and allowed to dry. All bare patches must be primed with First Choice Water Based Alkali Resistant Plaster Primer and allowed to dry for 4-6 hours. In the case of boards or panels, all metal areas/nail heads, etc. should be spot primed with Warrior Metal Etch Primer.

Gloss or semi-gloss surfaces must always be sanded down with a fine abrasive to provide a good key for subsequent coats and then primed with First Choice Universal Undercoat and allowed to dry for 16 hours.

Finish off with at least 2 coats of First Choice Acrylic PVA in colour of choice allowing 4 hours drying time between coats.

PROPERTIES:

APPLICATION:	Brush or Roller
CLEANING SOLVENT:	Water
THINNING SOLVENT:	Do not thin - ready for use
SPREADING RATE:	PRIMER COAT: ± 4-6 m ² per litre TOP COATS: ± 6-8 m ² per litre
DRYING TIMES:	SURFACE DRY: 1 hour TOUCH DRY: 4 hours OVERCOATING: 4 hours
SCRUB RESISTANCE:	Washable surface (>10 000 Oscillations)
PACK SIZE:	1L, 5L, 20L
COLOUR RANGE:	White, Pastel, Deep, and Ultra Deep
RELATIVE DENSITY	1.45 ± 0, 05 kg per litre
VISCOSITY:	120-125 KU
FLASH POINT:	Non flammable



GENERAL INFORMATION:

- a) It is important that this product be thoroughly mixed with a flat paddle before use.
- b) As per standard painting practices, no painting should take place if surface or ambient temperatures are below 10°C or above 30°C. Painting should cease at 3pm or when rain is imminent.

DISCLAIMER

The recommendations contained herein are given in good faith and are meant as a guide for specifiers and users. They are based on laboratory tests and practical historical experience. No guarantee or warranty is implied by the recommendations contained in the Technical Data Sheet as conditions of use, application method, cleanliness and soundness of the substrate are beyond our control.

N.B. Technology may change with time necessitating changes to the Technical Data Sheet (TDS). It is the specifiers and users responsibility to ascertain that the latest TDS is being used.

WARRIOR PAINTS AND COATINGS (PTY) LTD (REG NO. 1987/003946/07)
45 FRANS DU TOIT STREET
P O BOX 911-1181
ROSSLYN 0200
SOUTH AFRICA

HELP DESK
EMAIL: info@warriorpaints.co.za
TEL: +27 12 5413596
FAX: +27 12 541 1434
www.warriorpaints.co.za